CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-12-20-111** **Date: 10/11/2018**

Customer : Assistant Executive Engineer, Yelahanka Satellite Town Sub Division, BBMP, Bangalore.

Address : Yelahanka Satellite Town Sub Division, BBMP, Bangalore.

Project Name : Intimation of Work Order to Start the Work of Providing Sign Board and Ornamental Boards A Sector and B Sector and Other Area in Ward No 04

Agency : Sri.N.Shivakumar No:96,KHB Colony,Gandhinagara, Yelahanka Bangalore-64.

Customer's Reference : EE(YNK.D)E-PMT-21/WO/000069/2019-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-11-18

Customer ID : M20 CONCRETE

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/11/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 CONCRETE	M20	03/11/2018	10/11/2018	150.41 X 149.13 X 149.55	22431	**8.965**	417.0	18.6	18.7
2	M20 CONCRETE	M20	03/11/2018	10/11/2018	150.22 X 151.03 X 151.01	22687	**8.698**	425.3	18.7	
3	M20 CONCRETE	M20	03/11/2018	10/11/2018	150.83 X 150.64 X 149.80	22721	**8.403**	425.7	18.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL PRO BANGALORE Sig..... Date.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****